




# ANHUI HANHAI NEW MATERIAL CO., LTD.

www.ahmagnet.com | Tel.: +86-755-82821802 | E-mail: support@ahmagnet.com

Standard Sintered NdFeB (Neodymium Magnets)

**N50M**

Characteristic	Units	Min	Max
		Br	T
Hcb	KGs	14.0	14.3
	kOe	≥13.3	
Hcj	kA/m	≥1060	
	kOe	≥14	
BH Max	kA/m	≥1114	
	MGOe	47	51
	kJ/m <sup>3</sup>	374	406
α (Br)	%/°C	-0.11	
β (Hcj)	%/°C	-0.68	
Max Temperature	°C	≤100	
Density	g/cm <sup>3</sup>	7.60	



**Notes** The material data and demagnetization curves shown above present typical. properties that may vary due to product size, shape and coating.

Additional grades and customized magnets are available. Please contact us for more information.

Address: Zongsi Road, Economic and Technology Development Area, Luan City, Anhui Province, 23700, China.