




ANHUI HANHAI NEW MATERIAL CO., LTD.

www.ahmagnet.com | Tel.: +86-755-82821802 | E-mail: support@ahmagnet.com

Standard Sintered NdFeB (Neodymium Magnets)

N35H

Magnetic Properties	Characteristic	Units	Min	Max
	Br		T	1.18
		KGs	11.8	12.4
Hcb		kOe	≥11.0	
		kA/m	≥877	
Hcj		kOe	≥17	
		kA/m	≥1353	
BH Max		MGOe	33	37
		kJ/m ³	263	295
	α (Br)	%/°C	-0.12	
	β (Hcj)	%/°C	-0.65	
	Max Temperature	°C	≤120	
	Density	g/cm ³	7.55	



Notes The material data and demagnetization curves shown above present typical. properties that may vary due to product size, shape and coating.

Additional grades and customized magnets are available. Please contact us for more information.

Address: Zongsi Road, Economic and Technology Development Area, Luan City, Anhui Province, 23700, China.