




ANHUI HANHAI NEW MATERIAL CO., LTD.

www.ahmagnet.com | Tel.: +86-755-82821802 | E-mail: support@ahmagnet.com

Standard Sintered NdFeB (Neodymium Magnets)

N48UH

Characteristic	Units	Min	Max
		Br	T
Hcb	KGs	13.6	14.0
	kOe	≥12.6	
Hcj	kA/m	≥1011	
	kOe	≥25	
BH Max	kA/m	≥1990	
	MGOe	45	49
	kJ/m ³	358	390
α (Br)	%/°C	-0.115	
β (Hcj)	%/°C	-0.50	
Max Temperature	°C	≤180	
Density	g/cm ³	7.55	



Notes The material data and demagnetization curves shown above present typical. properties that may vary due to product size, shape and coating.

Additional grades and customized magnets are available. Please contact us for more information.

Address: Zongsi Road, Economic and Technology Development Area, Luan City, Anhui Province, 23700, China.