




ANHUI HANHAI NEW MATERIAL CO., LTD.

www.ahmagnet.com | Tel.: +86-755-82821802 | E-mail: support@ahmagnet.com

Standard Sintered NdFeB (Neodymium Magnets)

N38AH

Characteristic	Units	Min	Max
		Br	T
	KGs	12.2	12.6
Hcb	kOe	≥11.4	
	kA/m	≥915	
Hcj	kOe	≥35	
	kA/m	≥2786	
BH Max	MGOe	36	40
	kJ/m ³	287	318
α (Br)	%/°C	-0.112	
β (Hcj)	%/°C	-0.45	
Max Temperature	°C	≤230	
Density	g/cm ³	7.60	



Notes The material data and demagnetization curves shown above present typical. properties that may vary due to product size, shape and coating.

Additional grades and customized magnets are available. Please contact us for more information.

Address: Zongsi Road, Economic and Technology Development Area, Luan City, Anhui Province, 23700, China.